

| MANUAL SECTION | ISSUE DATE | AUTHORISED | REPLACES | PAGE |
|----------------|------------|------------|----------|------|
|----------------|------------|------------|----------|------|

| | | | | |
|-----------------|------------------|-----------|-----------------|---------------|
| <i>Flooring</i> | <i>July 2006</i> | <i>PM</i> | <i>Oct 2003</i> | <i>1 of 3</i> |
|-----------------|------------------|-----------|-----------------|---------------|

AQUACOLOUR Epoxy Enamel

GENERIC TYPE:

Water-borne, two-pack epoxy coating giving good durability, gloss, and abrasion resistance.

**PROPERTIES/
FEATURES:**

- Excellent flow and levelling properties
- Excellent adhesion to most substrates damp and dry
- Long pot life
- **Non-flammable**
- Heat resistance – up to 100°C
- Abrasion resistance – excellent
- Pencil hardness – 6H
- Flexibility (6mm mandril) – pass
- **Finish – full gloss only**
- Solids volume – 40% mixed
- SG – 1.3 Kg/L mixed
- Extremely hard tile-like finish
- **Non-toxic** when cured; **Low odour** during application
- Great ease of use (water based)
- Weathering – some chalking will occur in time but will maintain good film integrity
- May be overcoated with solvent epoxies and polyurethanes
- Colour – white. May be factory tinted to limited range of pastels. Also available in a clear finish as **Aquaseal**.
- Maximum humidity during application – 85%. Requires good ventilation and air movement to aid drying

SUGGESTED USED

- Abrasion, chemical, stain, graffiti resistant surface for toilet partition and wall and floor coatings, food and chemical processing plants. Will withstand cleaning with aggressive solvents to remove graffiti, etc. Also suitable for frequent washing with hot water and detergents.
- As gloss finish coat in SITUCLAD E system for food processing areas (refer that data)
- Will form a waterproof membrane / flooring when used in conjunction with **Aquaguard 101**.

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer. CERTIFIED ISO 9001 REG. NO. 158

This document is a technical data information sheet The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS www.nuplexconstruction.co.nz

| | | | | |
|-------------------------|-------------------------|-------------------------|----------------------------|---------------------|
| H A M I L T O N | PALMERSTON | NORTH | W E L L I N G T O N | CHRISTCHURCH |
| Telephone: 0-7-847 8658 | Telephone: 0-6-353 3685 | Telephone: 0-4-477 7040 | Telephone: 0-3-366 6802 | |
| Fax: 0-7-847 3766 | Fax: 0-6-353 3632 | Fax: 0-4-477 7039 | Fax: 0-3-379 0279 | |

AQUACOLOUR (cont'd)

- Production line coating for fibre cement sheeting, primed steel, aluminium or galvanised iron
- High performance finish coating for industrial protection on the outside of chemical transport and storage tanks
- Air dry enamel finish for metal cabinets and claddings, particle board, plywood etc
- Slip resistant floor coatings.

NOT RECOMMENDED:

- Continuous immersion in strong acids, alkalies or aggressive solvents
- Contact with water within 36 hours after application
- Application in very cold, damp, unventilated conditions. (use Terratuff in these situations)

CHEMICAL RESISTANCE:

| | |
|---------------------------------------|-----------|
| Water resistance 25°C | Excellent |
| Water resistance 100°C | Good |
| 10% Hydrochloric acid | Good |
| 10% Acetic acid | Good |
| 10% Sulphuric acid | Good |
| 10% Caustic Soda | Excellent |
| Xylene | Excellent |
| MEK | Fair |
| Salt Spray ASTM B117-57T (1000 hours) | Good |

APPLICATION METHOD:

Caution: If applying over Aquaguard 101, to achieve good intercoat adhesion, ensure the AG101 is cured 48hrs prior to Aquacolour application. Brush, roller, conventional and airless spray; roller is normal. Roll evenly to achieve a consistent effect. Thin slightly if necessary.

Ensure good cross air flow to ensure good drying. A hard finish is obtained after 48 hrs.

MIX RATIOS:

4 parts A/ 1 part B, mix with electric drill and mixer

COVERAGE RATES:

8m²/litre/coat; Two coats recommended.

SLIP RESISTANT FINISHES:

Slip resistant finishes can be achieved using:

| | <u>Application Weight</u> |
|---|------------------------------|
| Revtred (glass beads) | 50m ² /550gm pack |
| Microcells (ceramic sphere) | 100gms/4 litres |
| J61 Sand (fine sand) | 2 kgs/m ² |
| Typical co-efficient of friction "wet" NZS/AS3661.1:1993: | |
| Revtred | 0.54 |
| Microcells | 0.56 |
| J61 Sand | 0.63 |

Note:

Additive is applied to the second to last coat.

AQUACOLOUR (cont'd)**FILM BUILD:**

- 125 micron wet/coat = 50 micron dry/coat
- Recommended 250 microns wet = 100 microns dry
- Number of coats – minimum two
- Note: These figures are based on undiluted material. Allowances must be made based on the rate of dilution. Also allow for application losses and surface irregularities.

THINNING:

Dilution – 5-10% with clean potable water. Also use meths for a strong diluent effect.

DRY TIMES:

| | |
|---|---------------|
| Pot life | 8 hrs at 20°C |
| Touch Dry | 4 hrs |
| Recoat | Overnight |
| Unaffected by water | 48 hrs |
| Full cure | 7 days |
| Minimum application temperature - +10°C | |

CLEAN UP:

Warm water and detergent. Final clean with Methylated Spirits, Kerosene, or Nuplex brush cleaner

CAUTION:

- Relative humidity must not exceed 85% during application or subsequent cure. Ensure continuous crossflow ventilation to ensure dry & cure.
- Although this product is waterbased still use a suitable respirator when using in confined areas or spray applying.
- Care should be taken to avoid prolonged skin contact. Wash contaminated skin with soap and water and change contaminated clothing promptly.
- Ensure MSDS sheets are displayed on site.

SHELF LIFE

24 months in unopened containers. Store above 2°C.

PACKAGING

Part A – 8 Litre pails; Part B – 2 Litre pails

FLASHPOINT

None

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer. CERTIFIED ISO 9001 REG. NO. 158

This document is a technical data information sheet The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS www.nuplexconstruction.co.nz

| | | | |
|-------------------------|-------------------------|-------------------------|-------------------------|
| H A M I L T O N | PALMERSTON NORTH | W E L L I N G T O N | C H R I S T C H U R C H |
| Telephone: 0-7-847 8658 | Telephone: 0-6-353 3685 | Telephone: 0-4-477 7040 | Telephone: 0-3-366 6802 |
| Fax: 0-7-847 3766 | Fax: 0-6-353 3632 | Fax: 0-4-477 7039 | Fax: 0-3-379 0279 |