



Ren:C:0-Thane® Polyurethanes

RP 6444 R/H

A SEMI-RIGID, SHORE 60±5D ELASTOMER

Ren® RP 6444 resin and hardener is an extremely effective semi-rigid, light amber, two-component polyurea elastomer for applications in which wear resistance is critical. RP 6444 R/H develops excellent physical properties when cured at room temperature without containing MOCA, TDI, or MDA. The low viscosity and good working life allows easy handling and release of trapped air.

MIX RATIO

Resin to Hardener	By Weight:	By Volume:
	100 to 60	100 to 60

TYPICAL HANDLING PROPERTIES*

	<u>ASTM Method</u>	<u>Resin</u>	<u>Hardener</u>	<u>Mixed</u>
Color	Visual	Light yellow	Amber	Amber
Specific Gravity	D-1963	1.04	1.06	
Viscosity, cP	D-2393	7,500	95	2,500
Gel Time, 4fl. oz, minutes	D-2471			27

NOTE: These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Product Management Department.

RECOMMENDED CURE SCHEDULE

1. 77°F (25°C) at 7 days

TYPICAL CURED PROPERTIES*

	<u>ASTM Method</u>	<u>Cure 1 Value</u>
Density, lb./ft ³ (g/cm ³)	D-792	66(1.05)
Cubic Inch per Pound		26.4
Hardness, Shore D	D-2240	60 ± 5
Ultimate Tensile Strength, psi	D-638	3,400
% Elongation	D-638	325
Tear Strength, psi	D-624	550
Linear Shrinkage, in/in**	D-2566	0.001

* Tested @ 77°F (25°C) unless otherwise noted.

** Molds are half round steel, 10 inches long, 0.875 inches deep

SAFETY: Do not use or handle this product until the Material Safety Data Sheet has been read and understood.

IMPORTANT: The following supercedes Buyer's documents. **SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential, or indirect damages for alleged negligence, breach of warranty, strict liability, tort, or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer.

This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS

PO Box 12841, Penrose, Auckland Telephone 0-9-579 2029 Fax 0-9-579 3709 www.nuplexconstruction.co.nz email: bpdsales@nuplex.co.nz

H A M I L T O N	P A L M E R S T O N N O R T H	W E L L I N G T O N	C H R I S T C H U R C H
Telephone 0-7-847 8658	Telephone 0-6-553 3685	Telephone 0-4-477 7040	Telephone 0-3-366 6802
Fax 0-7-847 3766	Fax 0-6-353 3632	Fax 0-4-477 7039	Fax 0-3-379 0279