

MANUAL SECTION	ISSUE DATE	AUTHORISED	REPLACES	PAGE
Construction Products	October 2008	PM	Sept 2002	1 of 2

TRUESTIK EA FLEXIBLE EPOXY ADHESIVE

Based on Nuplex Epoxy Technology

DESCRIPTION:

Truestick EA is a flexible epoxy adhesive with good handling properties for many applications.

FEATURES

- Trowelable consistency
- 3:1 mix ratio
- Water resistant
- Excellent adhesion

BENEFITS

- Easier to apply but won't run
- Simple ratio
- Wet area use
- Many uses to many substrates

NORMAL END USES:

- Bonding timber, furniture, flooring
- Bonds fibreglass, concrete and metals
- Laminates ply
- Flooring adhesive for **rubber** to concrete or timber
- Flooring adhesive for timber flooring
- Flooring adhesive for most rigid vinyl tiles and vinyl sheet

TYPICAL PROPERTIES:

	<u>RESIN</u>	<u>HARDENER</u>
Appearance:	Green Gel	Amber Liquid
Specific Gravity:	1.65	1.0
Flash Point:	>100°C	>100°C
Shelf Life:	>24 months	>24 months

MIX RATIO:

	<u>by weight</u>	<u>by volume</u>
Resin	3	3
Hardener	1	1

POT LIFE:

(Usable Life)

@ 15°C **@ 20°C**
 100-140 minutes 60-80 minutes
 Pot life is shortened if material is held in bulk (spread out to prevent heat build up).
 24 hours at normal ambient conditions

CURE TIME:

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer. CERTIFIED ISO 9001 REG. NO. 158 This document is a technical data information sheet The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

TRUESTIK EA (cont'd)**COVERAGE:**

1. Use as volume required (0.001m³=1Lt)
2. 1Lt covers 1m² @ 1mm thick.
3. Rubber tiles require 3-5m²/mixed Lt.
4. Wooden flooring approx 2-3m²/mixed Lt.

SURFACE PREPARATION:

1. Timbers: sand with 80 grit to roughen.
2. Concrete: grind or acid etch.
3. Metals: grind to clean bright finish, wipe with Eposolve 70.
4. Rubbers pretreat with activators if required.

MIXING INSTRUCTIONS:

Carefully mix the product according to the stated mix ratio. The mix ratio is the only acceptable formula. Increased hardener levels result in a **weaker** product. Mix until uniform and no streakiness is evident.

APPLICATION:

Use above 12°C ambient temperature, ensure substrates are at that temperature. Apply mixed Truestik EA with spatula and clamp materials together overnight.

For bonding **rubber flooring**, apply the adhesive at the recommended spread rate with a notched trowel and **roll** flooring in the wet adhesive. Materials with a “memory” may need to be weighted down. For **timber flooring**, apply the mixed Truestik EA to the substrate with a notched trowel and apply the timber into the wet adhesive. **Vinyl tiles:** use a notched trowel and apply at 5m²/Lt. Roll heavily in all cases, **before** the adhesive sets.

HEALTH AND SAFETY:

Use gloves wherever possible. Wash hands with warm, soapy water after any skin contact. Re-seal all containers tightly. Clean up with Eposolve 70.

CURED PROPERTIES:

Maximum Operating Temperature:	50 - 60°C
Density kg/L:	1.05
Tensile Strength MPa:	12 - 16
Tensile Bond Strength MPa:	N/A
Flexural Strength:	30 - 40
Water Absorption % @ w/w:	0.7 - 0.9

OTHER EPOXY PRODUCTS:

K80	Pourable Grout	K214	General Purpose Adhesive
K102	H.V. Mortar	K36	Clear Laminating Resin
K125	Paste	K78	Crack Repair
K230	Fast Set Paste	K85	Rapid Set Pourable
K273	Low Temp Paste	K268	Rapid Set Paste
K106	Structural 24 hour Adhesive	Fairing Cream	Sandable Smoothing Paste
K219	Structural 5 minutes Adhesive		
K138	High Strength, Structural Heat Resistant Adhesive		
K2005	High Peel Strength, Structural Adhesive		
Repikit 310	Concrete Crack Repair Tube and Kit		